

Guiyang Talent Friction Material Co., Ltd.

9/F, D Building, Mei Di Cai Zhi Center, 8 North Chang Ling Rd, Guan Shan Hu District, Guiyang, Guizhou, China Tel: 0086 851 86612409 Fax: 0086 851 86612763

Fax: 0086 851 86612763 info@talfri-brake.com

Product Data Sheet: TRH3020

Product Description:

TRH3020 is a rigid molded Non Asbestos Brake Sheet of medium and high frictional coefficient. The flat sheet exhibits excellent resistance to heat and compression and outstanding stability in applications. TRH3020 sheet can be processed into segments or rings and other shapes by tooling or machining.

Applications:

TRH3020 is widely used in many industrial applications. It is not recommended for use on oil Immersed applications.

Dimension:

Length x Width: 762mm x 762mm (30inches x 30 inches)

Thickness: 3.2mm—22mm (1/8 – 7/8 inch)

Frictional Properties:

Normal	0.50
Hot	0.48
400°F	0.50

Recommended Operating Range:

Max. Pressure, psi 280 Max. Rubbing Speed, ft/min 5000

Max. Intermittent Temperature 650°F (340°C) Max. Continuous Temperature 600°F (315°C)

SAE J661a TEST CURVES



